



邦泰複合材料股份有限公司
PONTEX POLYBLEND CO., LTD.

TEL:886-4-25384121 FAX:886-4-25384120
 http://www.pontex.com

▶▶▶ Nylon / NRB5430G-BK1

產品資訊

Product Information

物理性質	PROPERTY	測試方法METHOD	單位UNIT	結果(數據)RESULT
機械性質 MECHANICAL				
抗張強度	Tensile Strength	ASTM D638	kg/cm ²	1200
伸長率	Elongation	ASTM D638	%	1.5
抗折強度	Flexural Strength	ASTM D790	kg/cm ²	1800
抗折模數	Flexural Modulus	ASTM D790	kg/cm ²	100000
衝擊強度	IZOD Impact, Notched 1/8" RT	ASTM D256	kg-cm/cm	8
	IZOD Impact, Notched 1/8"-20°C	ASTM D256	kg-cm/cm	
	IZOD Impact, Notched 1/8" -40°C	ASTM D256	kg-cm/cm	
硬度	Hardness – R Scale	ASTM D785	-	
硬度	Hardness – Shore D	ASTM D2240	-	
熱變形溫度	Heat Deflection Temp. 4.6kg/cm ²	ASTM D648	°C	-
	Heat Deflection Temp.18.6kg/cm ²	ASTM D648	°C	240
流動指數	Melt Index, g/10 min	ASTM D1238	-	70
成形收縮率	Mold Shrinkage	ASTM D955	cm/cm	0.15~0.35
比重	Specific Gravity	ASTM D792		1.40~1.44
灰分	Filler Content	ASTM D2584	%	34±2
含水率	Water Absorption	ASTM D570	%	≤0.1
耐燃性	Flammability 1/8"	UL 94	-	V-0

附註 Remark

※Typical properties can be subject to change without further notice.

ISO 9001 / ISO14001 ASSURANCE